

# JRA セラミックアンギュラベアリング

d	主要寸法			定格荷重 (参考)		呼び番号	許容回転数 (参考)	
	D	B	r (min)	Cr	Cor		グリス	オイル
	mm			kN			rpm	
10	26	8	0.3	4.72	2.14	7000	55900	75400
	30	9	0.6	5.23	2.54	7200	53300	71500
	35	11	0.6	9.50	4.40	7300	39000	52000
12	28	8	0.3	5.23	2.54	7001	50700	67600
	32	10	0.6	7.02	3.31	7201	46800	63700
	37	12	1.0	10.80	6.17	7301	35100	45500
15	32	9	0.3	5.99	3.24	7002	44200	58500
	35	11	0.6	8.90	4.80	7202	41600	54600
	42	13	1.0	13.30	6.89	7302	36400	49400
17	35	10	0.3	6.89	3.82	7003	40300	53300
	40	12	0.6	10.50	5.64	7203	37700	49400
	47	14	1.0	15.30	8.05	7303	33800	45500
20	42	12	0.6	9.95	5.74	7004	35100	46800
	47	14	1.0	14.00	7.84	7204	32500	44200
	52	15	1.1	17.90	9.62	7304	29900	40300
25	47	12	0.6	11.10	7.08	7005	29900	40300
	52	15	1.0	15.90	9.80	7205	27300	36400
	62	17	1.1	27.00	15.60	7305	24700	33800
30	55	13	1.0	14.30	9.84	7006	26000	33800
	62	16	1.0	22.10	14.10	7206	23400	31200
	72	19	1.1	30.90	19.40	7306	20800	28600
35	62	14	1.0	18.20	13.10	7007	22100	29900
	72	17	1.1	29.10	19.20	7207	20800	27300
	80	21	1.5	38.90	24.90	7307	18200	24700
40	68	15	1.0	18.70	14.20	7008	19500	27300
	80	18	1.1	36.80	25.40	7208	18200	24700
	90	23	1.5	50.30	34.00	7308	16900	22100
45	75	16	1.0	23.10	18.30	7009	18200	24700
	85	19	1.1	34.60	24.70	7209	16900	22100
	100	25	1.5	60.30	42.10	7309	14300	19500
50	80	16	1.0	23.70	19.70	7010	16900	22100
	90	20	1.1	40.80	30.30	7210	15600	19500
	110	27	2.0	70.60	50.00	7310	13000	18200
55	90	18	1.1	30.30	25.70	7011	15600	19500
	100	21	1.5	50.60	38.20	7211	14300	18200
	120	29	2.0	91.00	63.40	7311	12220	16900
60	95	18	1.1	34.70	29.50	7012	14300	18200
	110	22	1.5	55.80	42.90	7212	12610	16900
	130	31	2.1	101.00	73.40	7312	11310	15600
65	100	18	1.1	38.00	33.70	7013	12870	16900
	120	23	1.5	66.00	52.10	7213	11700	15600
	140	33	2.1	114.00	73.60	7313	10530	14300
70	110	20	1.1	45.80	41.10	7014	11960	15600
	125	24	1.5	69.40	57.00	7214	10790	14300
	150	35	2.1	128.00	96.30	7314	9750	13000
75	115	20	1.1	46.80	43.80	7015	11180	14300
	130	25	1.5	75.30	62.80	7215	10140	13000
80	125	20	1.1	57.50	51.00	7016	10400	14300
	140	26	2.0	85.00	73.60	7216	9490	12610
85	130	22	1.1	55.10	52.90	7017	9880	13000
	150	28	2.0	94.90	80.80	7217	8970	11830
90	140	24	1.5	65.00	62.80	7018	9230	12350
95	145	24	1.5	67.20	66.00	7019	8840	11700
100	150	24	1.5	73.80	73.10	7020	8320	11180

- 【備考】 1. 上記定格荷重、許容回転数は、窒化珪素材軸受の参考値を示す。  
 2. ジルコニア材の軸受の定格荷重は、上記の75～80%を参考値としてください。